



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
http: //www. chamaeleon/produktion.de

TECHNICAL DATA SHEET

CHAMÄLEON WHEEL PAINT (SILVER)

Article number:	26104
Intended use:	Car refinishing Product/ Lacquer
General characteristics:	For embellishing and repairing of steel and light metal rims and hubcaps.
Product characteristics:	<ul style="list-style-type: none">▪ Fast drying▪ Good coverage▪ Resistant to petrol, chemicals and weather influences▪ Non-fading and UV-resistant▪ Lasting gloss▪ Good surface hardness▪ Wear-resistant and scratch free▪ Excellent adhesion
Technical characteristics:	
Contents:	500 ml
Base:	Acrylic resin
VOC-content:	Approximately 90% w/w
Solid content:	Approximately 10% w/w
Coverage:	4 to 5 rims / hubcaps Approximately 1 rim / hubcap
Dust dry:	After 5 to 10 minutes
Tack free:	After 10 to 20 minutes
Hardened/re-sprayable:	After 2 hours
Heat resistant:	To 110°C

Usage:

Before use, carefully read the directions on the packaging and act accordingly.



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Pre Treatment:

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of Chamäleon Spray Primer suitable for the surface. After drying, sand the base layer (grain 600).

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Application:

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use:

clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Package: 500 ml

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:
e-mail: info@chamaeleon-produktion.de
See information on safety in Safety Data Sheet.*