



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

TECHNICAL DATA SHEET

CHAMÄLEON HEAT RESISTANT SPRAY

Article number:	26601 (Black), 26602 (Silver),
Intended use:	Car refinishing Product/ Preparation
General characteristics:	High quality lacquer to treat surfaces, treated and untreated, which are exposed to very high temperatures.

Product characteristics:

- Heat resistant
- Excellent adhesion
- Resistant to petrol, chemicals and weather influences

Physical and Chemical

Contents
Base
VOC-content
Solid content
Gloss
Coverage
Dust dry Tack
free Hardened
Heat resistant

Characteristics

400 ml
Silicone resin
Approximately 84% w/w
Approximately 16% w/w
Satin matt
1,25 to 1,75 m²
After 5 to 10 minutes
After 10 to 15 minutes
After 30 to 60 minutes (160°C)
To 800°C

Usage:

Before use, carefully read the directions on the packaging and act accordingly.
Chamäleon GmbH – Technical Data Sheet



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Pre Treatment:

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Do not apply any primer.

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the heat resistant lacquer in several thin layers. Before applying the next layer, again shake the aerosol. Allow to dry at room temperature for one hour. Then, heat for 30 to 60 minutes (160°C) in order to harden the paint layer. Smoke develops during the lacquer hardening process.

After use:

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:
e-mail: info@chamaeleon-produktion.de
See information on safety in Safety Data Sheet.*