



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

TECHNICAL DATA SHEET

CHAMÄLEON SPRAY PUTTY

Article number:	26701
Intended use:	Car refinishing Product/ Preparation
General characteristics:	High quality, fast-drying filler to fill small irregularities in surfaces, treated and untreated, of wood, metal and aluminum. Suitable primer as pre treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers).
Product characteristics:	<ul style="list-style-type: none">• Fast drying• Excellent coverage• Corrosion preventive• Easy to sand, both wet and dry (from grain 400)• Excellent filling property• Good adhesion• Re-sprayable with all lacquer systems

Physical and Chemical

Contents
Base
Colour
VOC-content
Solid content
Gloss
Coverage
Dust dry
Tack free
Hardened/resprayable
Heat resistant

Characteristics

400 ml
Acrylic resin
Beige-yellow
Approximately 75% w/w
Approximately 25% w/w
Satin matt
1,25 to 1,75 m²
After 5 to 10 minutes
After 10 to 20 minutes
After 2 hours
To 110 °C

Usage:



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment:

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeter.

Apply the filler in several thin layers. Before applying the next layer, again shake the aerosol.

After use:

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:
e-mail: info@chamaeleon-produktion.de*



See information on safety in Safety Data Sheet.

Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>