



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

TECHNICAL DATA SHEET

ZINC SPRAY

Article number: **26722**

Intended use: Car refinishing Product/ Priming/ Lacquer

General characteristics: Zinc Alu Primer for zinc-plated parts and surfaces, which have been damaged by welding, sanding, drilling, transportation etc., and which have to be repaired or adapted to colour shade. Also suitable as excellent corrosion protection for metal surfaces and black iron metals. Suitable for only a limited extent on aluminium. For bigger metal surfaces, which are especially exposed to corrosion, use Zinc Spray.

Quality and properties:

- Rust-protecting
- Heat-resistant up to 300°C
- Resistant to changing temperatures
- Good flow
- Coatable with air-drying acrylic, nitro-combi and synthetic lacquers

Physical and chemical characteristics:

- **Basis of the binder:** Epoxyester
- **Colour:** silver-metallic, similar to galvanizing
- **Smell:** solvent
- **Degree of gloss:** satin matt, not measurable, as metallic
- **Efficiency:** Depending on consistence and color of the ground: 400 ml are sufficient for approx. 1.5 m² at covering layer
- **Drying time** (at 20°C, 50% relative air humidity):
 - Dust-dry: after approx. 15 minutes
 - Dry to touch: after approx. 60 minutes
 - Cured: after approx. 12 hours
 - The drying time depends on surrounding temperature, air humidity and thickness of the applied coat.
- **Temperature resistance:** up to 300°C
- **Storage stability:** 10 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)
- **Size:** aerosol cans, maximum nominal volume 400 ml



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Environment and labelling:

Environmentally sound: Zinc Alu Spray is 100% free of heavy metals. The caps and packagings are made of recyclable material.

Disposal: Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling: All products comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

Using instructions:

Before use, carefully read and observe the warning texts on the label!

Application

- The ground has to be clean, dry and free from rust and fat.
- Shake can vigorously for approx. 2 minutes.
- Test spray at an invisible spot.
- Apply several covering coats.
- Spray from a distance of approx. 25 cm.
- Can be coated with itself. It is possible before and to apply a top coat.

Data: 4, September 2014

This release replaces all eventually earlier issued versions.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier: e-mail: info@chamaeleon-produktion.de
See information on safety in Safety Data Sheet.*