

Chamäleon GmbH Rudolf-Diesel-Straße, 8a 69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon-produktion.de

http://www.chamaeleon-produktion.de

TECHNICAL DATA SHEET Revision date: 20.04.2018

## **LEATHER PAINT SPRAY**

26801 **Article number:** 

**Intended use:** Car refinishing product/ Colour spray for smooth

**Product description:** High quality leather spray to repair and embellish

parts of leather, vinyl and artificial leather.

**Product characteristics:** 

Lasting colour and lasting gloss

Elastic

**Excellent adhesion** 

Maintains the original structure

## **Physical and Chemical Characteristics:**

Contents: 200 ml

Nitro-cellulose binder Base: VOC-content: Approximately 84% w/w Solid content: Approximately 16% w/w

Satin matt Coverage: 0,50 to 1,00 m<sup>2</sup> Gloss:

Dust free: After 5 to 10 minutes Tack free: After 10 to 20 minutes

After 2 hours Hardened/re-sprayable: Heat resistant: To 50°C

## Usage:

Before use, carefully read the directions on the packaging and act accordingly.

**Pre Treatment:** The surface should be clean, dry and free of grease.

## **Treatment:**

The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the vinyl spray in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.



Chamäleon GmbH Chamaleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon-produktion.de
http://www.chamaeleon-produktion.de

Data: 20, April 2018

This release replaces all eventually earlier issued versions.

For the additional information that is not included to the Technical Data Sheet apply to the supplier: e-mail: info@chamaeleon-produktion.de

See information on safety in Safety Data Sheet.