



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

## *TECHNICAL DATA SHEET*

### CHAMÄLEON BITUM SPRAY

<b>Article number:</b>	<b>37100</b>
<b>Intended use:</b>	Car refinishing Product/ Preparation
<b>General characteristics:</b>	High quality preservative to treat the underside of vehicles
<b>Product characteristics:</b>	<ul style="list-style-type: none"><li>• Remains flexible</li><li>• Excellent adhesion</li><li>• Resistant to weather influences</li><li>• Resistant to weak acids and bases</li><li>• Excellent corrosion prevention</li><li>• Sound-absorbing</li></ul>

#### **Physical and Chemical**

Contents  
Colour  
VOC-content  
Dust dry

#### **Characteristics**

500 ml  
Black  
Approximately 70% w/w  
After approximately 60 minutes

#### **Usage:**

Before use, carefully read the directions on the packaging and act accordingly.

#### **Pre Treatment:**

Remove loose old lacquer and rust and sand the surface.

#### **Treatment:**

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the undercoating in several layers.



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

**After use:**

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:  
e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*