



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
<http://www.chamaeleon-produktion.de>

TECHNICAL DATA SHEET (Provisional)

## LASER Perfect Finish Liquid Compound

### Product Description

LASER Perfect Finish Liquid Compound was developed specifically for use on all modern original and refinish paint systems: medium solids (fresh – well cured) & high solids (fresh – cured). Perfect Finish can be used as a second step with all LASER cutting compounds to improve the final finish. Perfect Finish liquid has a mild cutting action.

### Product Information

Size	Product Code	Carton Quantity
500g	49902	12pcs

### Applications

Use with foam and wool applicators

### Characteristics

- Water based
- Silicone free
- High gloss
- Recommended with foam applicators
- Ready to use.
- Dry use

### Physical Properties

State	Liquid
Colour	White
Relative Density	1.00
Viscosity	11000cps
Flash Point	>93°C

*For the additional information that is not included to the Technical Data Sheet apply to the supplier: e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
<http://www.chamaeleon-produktion.de>

pH	7-9
VOC Content g/l	Refer to SDS

### Storage & Handling

Store at room temperature  
Protect from frost  
Shake container prior to use

### Directions For Use

#### *Step 2: Polishing*

1. Attach the Polishing Foam to a polishing machine and start slowly at a free running speed of 1000rpm and increase slowly up to 2000rpm.
2. Apply a small amount of LASER Perfect Finish to the paint surface and spread uniformly over the surface using the Polishing Foam before starting the machine to reduce splatter
3. Run lightly over the polishing area with the Polishing Foam kept flat until the desired gloss level has been achieved.
4. Remove any residue with a Finishing Cloth.

### Additional Information

Professional users may refer to the Safety Data Sheet for this product.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier: e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*